# WHITE CYPRESS

## GL10 White Cypress Glulam







- A highly durable Australian softwood timber which is found in Victoria, Western New South Wales and central Western Queensland.
- Timbers are ideal for exposed and internal applications such as timber fins, pergolas, columns and rafters.
- In contrast to the creamy white sapwood, the heartwood ranges in colours light yellow and orange to light brown, with occasional dark brown streaks.
- The grain is generally straight with a very fine and even texture.

#### **DURABILITY**

Durability Class 1 Plantation Softwood Available in untreated Available Cambered (600 m radius) and Straight

#### **GRADE APPEARANCE**

A grade appearance

#### PROPERTY PERFORMANCE

Stress Grade GL10 Bending Strength f'b = 22MPa Tension Strength f't = 11MPa Shear Strength f's = 3.7MPaCompression Strength f'c = 26MPa Modulus of Elasticity E = 10,000MPa Modulus of Rigidity G = 670MPa Density 700 kg/m³

### SIZES\*

Standard sizes are based on timber width (mm) and height (mm) measurements. Length (m) are measured in metres between 0.9m and 18.0m. Vicbeam can manufacture measurements outside standard sizes upon request.

W X H (Standard sizes)

40 x 126, 168, 210, 252, 294, 336

65 x 126, 168, 210, 252, 294, 336, 378, 420, 462,

504, 546, 588 ,630

85 x 126, 168, 210, 252, 294, 336, 378, 420, 462,


504, 546, 588 ,630

110 x 126, 168, 210, 252, 294, 336, 378, 420, 462,

504, 546, 588 ,630

130 x 126, 168, 210, 252, 294, 336, 378, 420, 462,

504, 546, 588 ,630



## Orders or Enquiries

Phone: 1300 788 705 Fax: (03) 9923 6791 Email: sales@vicbeam.com.au Website: www.vicbeam.com.au

