BLACKBUTT HARDWOOD

GL18 Blackbutt Hardwood Glulam







OVERVIEW

- Blackbutt is commonly available from New South Wales and Southern Queensland.
- A strong and durable timber that can be used for a range of structural, exterior and interior applications.
- Has an even texture and generally straight grain making it appealing for interior use applications.
- The heartwood ranging from golden yellow to pale brown, although occasionally a slight pinkish colour may be present.

DURABILITY

Durability Class 1 above ground Plantation Hardwood BAL 29 rating Available in untreated only Available Cambered (600 m radius) and Straight

GRADE APPEARANCE

A grade appearance

PROPERTY PERFORMANCE

Glulam Grade GL18 Bending Strength f'b = 50MPa Tension Strength f't = 25MPa Shear Strength f's = 5.0MPaCompression Strength f'c = 50MPa Modulus of Elasticity E = 18,500MPa Modulus of Rigidity G = 1,230MPa Density 900 km/m3

SIZES*

Standard sizes are based on timber width (mm) and height (mm) measurements. Length (m) are measured in metres between 0.9m and 18.0m. Vicbeam can manufacture measurements outside standard sizes upon request.


W X H (Standard sizes)

65 x 120, 150, 180, 210, 240, 270, 300, 330, 360, 390, 420

85 x 120, 150, 180, 210, 240, 270, 300, 330, 360, 390, 420, 450, 480, 510, 540, 570, 600

115 x 120, 150, 180, 210, 240, 270, 300, 330, 360, 390, 420, 450, 480, 510, 540, 570, 600

135 x 120, 150, 180, 210, 240, 270, 300, 330, 360, 390, 420, 450, 480, 510, 540, 570, 600



Orders or Enquiries

Phone: 1300 788 705 Fax: (03) 9923 6791 Email: sales@vicbeam.com.au Website: www.vicbeam.com.au

