

DURABEAM

GL10 White Cypress Glulam



- A highly durable Australian softwood timber which is found in Victoria, Western New South Wales and central Western Queensland.
- Timbers are ideal for exposed and internal applications such as timber fins, pergolas, columns and rafters.
- In contrast to the creamy white sapwood, the heartwood ranges in colours light yellow and orange to light brown, with occasional dark brown streaks.
- The grain is generally straight with a very fine and even texture.

DURABILITY

Durability Class 1
Plantation Softwood
Available in untreated
Available Cambered (600 m radius)
and Straight

GRADE APPEARANCE

A grade appearance

PROPERTY

Stress Grade
Bending Strength
Tension Strength
Shear Strength
Compression Strength
Modulus of Elasticity
Modulus of Rigidity
Density


PERFORMANCE

GL10
f_b = 22MPa
f_t = 11MPa
f_s = 3.7MPa
f_c = 26MPa
E = 10,000MPa
G = 670MPa
700 kg/m³

SIZES*

Standard sizes are based on timber width (mm) and height (mm) measurements. Length (m) are measured in metres between 0.9m and 18.0m. Vicbeam can manufacture measurements outside standard sizes upon request.

W	X	H (Standard sizes)
40	x	126, 168, 210, 252, 294, 336
65	x	126, 168, 210, 252, 294, 336, 378, 420, 462, 504, 546, 588, 630
85	x	126, 168, 210, 252, 294, 336, 378, 420, 462, 504, 546, 588, 630
110	x	126, 168, 210, 252, 294, 336, 378, 420, 462, 504, 546, 588, 630
130	x	126, 168, 210, 252, 294, 336, 378, 420, 462, 504, 546, 588, 630



Orders or Enquiries

Phone: 1300 788 705

Fax: (03) 9923 6791

Email: sales@vicbeam.com.au

Website: www.vicbeam.com.au

